


TEST REPORT

TEST NUMBER: 0295654

TEST METHOD CONDUCTED	ASTM D1308 Effect of Household Chemicals on Organic Finishes (Modified)
------------------------------	---



The four listed agents were applied to the wood finish and allowed to dwell for 4 hours. A diluted dish wash detergent was used as a first step of removal. If the stain persists, acetone was used to clean the area. The area was rated for any remaining discoloration from the stain application using the AATCC Grey Scale for staining.

STAINING AGENTS	RATING
Mustard	5.0
Shoe Polish	5.0
Black Sharpie	5.0
Used Motor Oil	5.0

APPROVED BY: Gary A. Curry

714 Glenwood Place Dalton, GA 30721 Phone: 706-226-3283 Fax: 706-226-6787 email: protest@optilink.us



TEST REPORT

DATE: 03-23-2023

Page 2 of 2

TEST NUMBER: 0295654

CLIENT	Lions Floor
--------	-------------

TEST METHOD CONDUCTED	ASTM D1308 Effect of Household Chemicals on Organic Finishes (Modified)
-----------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	District Pro: 2.5mm/12mil LVP
COLOR	East Aspen
ROLL NUMBER	SKU: LI-DP07
CONSTRUCTION	LVP



APPROVED BY:

Gary Anthony

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.