

Lions Floor

TEST REPORT

SCOPE OF WORK

SPC FLOORING

REPORT NUMBER

260714002SHF-011

TEST DATE(S)

2026-07-14 - 2026-08-20

ORIGINAL ISSUE DATE

2026-08-20

PAGES


6

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(January 13, 2025)

© 2025 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on the assigned page.
- 2.This report is invalid without an authorized person's signature.
- 3.This report is invalid if altered.
- 4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.
- 6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionalism of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.
- 7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.
- 8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.
- 9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.

Test Report

Original Issue Date: 2026-08-20

Intertek Report No. 260714002SHF-011

Applicant: Lions Floor

Address: 7300 somerset blvd,paramount, CA 90723

Attn: Jerry Guo

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification
SPC FLOORING	Lions Reservation Collection	182*1524*6.0mm(4.5mmSPC+1.5mmIXPE)
Sample ID	Sample Amount	Sample Received Date
S260714002SHF.032	50 pcs	2026-06-08
Sample Description		
182*1524*6.0mm (with 1.5mm IXPE underlayment)		

Test Methods And Standards

Test Standard	ASTM E492-25
Specification Standard	ASTM E989-21
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the applicant. Representativeness and authenticity of the submitted samples are responsibilities of the applicant.

Report Authorized



Ozzy Cheng Wilson Zhang
Name: Ozzy Cheng Name: Wilson Zhang
Title: Reviewer Title: Project Engineer

Test Report

Original Issue Date: 2026-08-20


Intertek Report No. 260714002SHF-011

Test Items, Method and Results:

Test Item: Laboratory Measurement of Impact Sound Transmission
 Test method: ASTM E492-25
 Temperature: 25 °C Relative Humidity: 60 %
 Volume of Source Room: 77 m³ Volume of Receiving Room: 112 m³
 Specimen area: 12.2 m²
 Floor Assemblies: The system consisted of 150mm thick concrete floor and the 6mm SPC FLOORING (including 1.5mm IXPE underlayment) were placed on the concrete floor.

Mounting of the specimen: Floating installation with click joints

Frequency (Hz)	Ln (dB)
100	60
125	61
160	63
200	63
250	60
315	59
400	53
500	50
630	48
800	46
1000	42
1250	39
1600	36
2000	34
2500	31
3150	29



Calculated Impact Insulation Class: IIC 56

Note:

1. Ln = Normalized Impact Sound Pressure Level
2. Classified IIC in accordance with ASTM E989-21, Standard Classification for Determination of Impact Insulation Class. This classification was used with one-third octave bands.
3. The IIC was for the whole floor assemblies.

Test Report

Original Issue Date: 2026-08-20

Intertek Report No. 260714002SHF-011

Appendix A: Test Photos



Test set up

Test Report

Original Issue Date: 2026-08-20

Intertek Report No. 260714002SHF-011

Appendix B: Sample Received Photo



SCAM FENGXIAN BR.

Revision:

NO.	Date	Changes
260714002SHF-011	2026-08-20	First issue