Lions Floor

TEST REPORT

SCOPE OF WORK
Coral Drift


REPORT NUMBER
260911002SHF-003

TEST DATE(S)
2026-09-11 - 2026-10-13

ORIGINAL ISSUE DATE
2026-10-13

PAGES
11

DOCUMENT CONTROL NUMBER
LFT-APAC-SHF-OP-10k(September 01, 2026)
© 2026 INTERTEK



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch

Test Report

Statement

1.This report is invalid without company's special seal for testing on the assigned page.

2.This report is invalid without an authorized person's signature.

3.This report is invalid if altered.

4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Partial reproduction of this report is prohibited without our written official approval. Any reproduced copy without reaffixing our test special seal shall be deemed invalid.

5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

6.Except for obligations, responsibilities and liabilities (if any) arising from the appropriateness and professionalism of the aforementioned testing, limited to the testing fee received, Intertek shall not bear any other obligations or liabilities.

7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the official report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.

8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.

9.The report was digitally signed by Intertek Group PLC, China - Shanghai. Please use Adobe Acrobat Reader to verify the authenticity.

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch
Plant 5 & 11(4F), No. 6958 Daye Road, Fengxian District, Shanghai, China
Tel: +86 21-61136116 Fax: 021-61189921
Website: www.intertek.com

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Applicant: Lions Floor

Address: 7300 somerset blvd， paramount， CA 90723

Attn: Jerry Guo

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification
Coral Drift	LI-OC02	1523*228*6.5+1.5mm/ white IXPE*10X
Sample ID	**Sample Amount**	**Sample Received Date**
S260911002SHF.001~007	10pcs	2026-08-26
Sample Description		**Brand**
1523*228*8mm		Ocean Crest

Test Methods And Standards

Test Standard	ANSI A326.3-2021, ISO 24337:2019, ASTM F410-08(2022), ASTM F3261-25a section 8.1, 8.3, 8.4, 8.5 and ASTM F1914-18(2023), ASTM F2199-20, ASTM F925-13(2020), ASTM F1514-19(2025)
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the applicant. Representativeness and authenticity of the submitted samples are responsibilities of the applicant.

Report Authorized

Flora Fan Roger Chen

Name: Flora Fan Name: Roger Chen

Title: Reviewer Title: Project Engineer

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Dynamic Coefficient of Friction

Test Method: ANSI A326.3-2021

Test Results:

Test Items	Test Method	Test Results	
Dynamic Coefficient of Friction	ANSI A326.3-2021	Dry condition: Wet condition:	0.71 0.43

Note:

1. Test item is subcontracted on accreditation by CNAS L1978.

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Size

Test Method: ISO 24337:2019

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Result:

Test item	Nominal value (mm)	Tested value (mm)	Tolerance (mm)
Length	1523	1523.0	0.0
Width	228	228.05	0.05

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Wear layer thickness

Test Method: ASTM F410-08(2022)

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Result:

Nominal value:	/	mm
Average value:	0.51	mm
Max. value:	0.51	mm
Min. value:	0.50	mm

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Residual indentation

Test Method: ASTM F3261-25a section 8.1 and ASTM F1914-18(2023)

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Condition:

Indenter:	Steel cylindrical foot	
Indenter diameter:	6.35	mm
Total load applied:	34	kg
Indentation time:	15	min
Recovery time:	60	min

Test Result:

Residual Indentation	Result (mm)
Specimen 1	0.03
Specimen 2	0.03
Specimen 3	0.05
Average value	0.04
Max. value	0.05

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Dimensional stability and curling

Test Method: ASTM F3261-25a section 8.3 and ASTM F2199-20

Conditioning:

Temperature:	23	°C
Relative humidity:	50	%
Duration:	24	h

Measure the initial length and curling

Test Condition:

Temperature:	70	°C
Duration:	6	h

Reconditioning:

Temperature:	23	°C
Relative humidity:	50	%
Duration:	24	h

Measure the final length and curling

Test Result:

Specimen	Dimensional stability (%)		Curling (in)
	Length direction/Machine direction	Width direction/Across machine direction	
1	-0.08	0.01	0.048
2	-0.08	0.01	0.048
3	-0.10	0.01	0.051
Average	-0.09	0.01	0.049
Max.	-0.10	0.01	0.051

Note:

1. Dimensional stability = (final length - initial length)×100/initial length

A negative value indicates shrinkage, and a positive value indicates expansion.

2. Curling = final curling - initial curling = Curl

Express the average value to the nearest 0.001in

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Resistance to Chemicals

Test Method: ASTM F3261-25a section 8.4 and ASTM F925-13(2020)

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Condition:

Duration of reagent contact: 60 min

Test Result:

Not affected

See below table for detailed test results

Detailed test results of Resistance to Chemicals

Reagent	Rating		
	Surface attack	Color change	Surface dulling
White vinegar (5% acetic acid)	0	0	0
Rubbing alcohol (70% isopropyl alcohol)	0	0	0
White mineral oil (medicinal grade)	0	0	0
Sodium hydroxide solution (5% NaOH)	0	0	0
Hydrochloric acid solution (5% HCl)	0	0	0
Sulfuric acid solution (5% H_2SO_4)	0	0	0
Household ammonia solution (5% NH_4OH)	0	0	0
Household bleach (5.25% NaOCl)	0	0	0
Olive oil (light)	0	0	0
Kerozene (K1)	0	0	0
Unleaded gasoline (regular grade)	0	0	0
Phenol (5% active phenol)	0	0	0

According to ASTM F925-13(2020), rating 0-3 represents:
0 = no change; 1 = slight change; 2 = moderate change; 3 = severe change.
Surface Dulling - Indicating that the specimen suffered from a loss of gloss,
Color Change - Indicating that the specimen suffered discoloration or bleaching, or both, and
Surface Attack - Indicating that the specimen suffered surface damage such as softening, warping, swelling, blistering, peeling, raised or rough area.

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Test Items, Method and Results:

Test Item: Resistance to heat

Test Method: ASTM F3261-25a section 8.5 and ASTM F1514-19(2025)

Conditioning: Condition the test specimens at (23 ± 2)°C and (50 ± 5)% relative humidity for at least 24h

Test Condition:

Temperature: 70 °C

Exposure time: 7 days

Spectrophotometer: Under D65 standard light source, 10° observer

Test Result:

Specimen	ΔE*	Average ΔE*
1	0.67	0.66
2	0.73	
3	0.59	

Test Photo:



After exposure

Test Report

Original Issue Date: 2026-10-13 Intertek Report No. 260911002SHF-003

Appendix A: Sample Received Photo



Revision:

NO.	Date	Changes
260911002SHF-003	2026-10-13	First issue